

Item	Description	Norm	UNIT	VALUE
Product	Article Code			TBK-2830
	Composition	UNI EN ISO 2076		100% Linear Filament Monoaxial Polyester Fibers
	Weight (fabric+coating)	UNI EN I12127	GR/SQM	280±10
	Colour			WHITE
	Finishing	ASTM 523	GLOSS UNIT	2,9 MATT (Gardner 60°)
	Fire reaction	DIN4102	CLASS	B1 flame retardant
	Thickness		MICRON	270±20
	Available Sizes			1,07-1,37-1,60*30m
Base Fabric	Weaving			WOVEN
	Pattern			PLAIN WEAVE
	Colour			WHITE
	Warp Yarn Count + Type	UNI EN ISO 2060	DENIER	300
	Weft Yarn Count + Type	UNI EN ISO 2060	DENIER	300
	Threads Warp	UNI EN ISO 1049-2	N°/INCHES	56
	Threads Weft	UNI EN ISO 1049-2	N°/INCHES	56
	Weight	UNI EN 12127	GR/SQM	150±10
	Warp Tensile Strength	UNI EN 13934-1	N	1500
	Weft Tensile Strength	UNI EN 13934-1	N	1100
	Warp Elongation	UNI EN 13934-1	%	25
	Weft Elongation	UNI EN 13934-1	%	25
	Yarn Tenacity	DIN EN ISO 2060	cN/dtex	3,7

Product description	Textile items in polyester are the ideal media to bear a huge quantity of coating, by keeping stable, without shrinkage or deformations, which may cause inconveniences in the final applications (printing and sewing). Blockout polyester is a double-side printable item, the inner black polyester layer prevents the passage of light by providing excellent shielding. In addition, blockout polyester canvas has a good abrasion resistance, a dimensional stability, an easy upkeep, a crease-proof quality, a low liquid-absorbing level; they all enable it to keep a good stability, also in case of a long-term exposure in high-humidity conditions.
Applications	Indoor applications for high definition fine art, pop-up, display and bifacial images applicable by using our TWO-TACK product. Outdoor applications: suitable for max. 12 months.
Printability	<p>Digital Printing: Laser printing and photocopy, plotters with eco-solvent, UV curable and latex inks.</p> <p>Screen Printing: eco-solvent, UV curable.</p> <p>Notes: due to the wide variety of UV inks products and digital printing machines, testing before printing is always recommended.</p>
Storage Period	24 months under ordinary condition at the temperature mean of 22 °C (min. 12 °C, max. 32 °C) and relative humidity of 45 - 65%. The material must stay in its box and does not have to be at sun light, otherwise the coating can be damaged.
REACH	Complying with the Italian Decree-Law nbr. 133 issued on 14.09.2009 and published on the Italian Gazzetta Ufficiale, we inform that the product comply with the REACH regulation with regard to the substances and chemicals used in their construction during manufacture. For further information, please refer to the certified copy available of the analyses worked out on the substances taken into consideration by REACH (Registration Evaluation Authorization of Chemicals).
Notes	Published information is based upon research and information which the Company believes to be reliable although such information does not constitute a warranty. Because of the variety of uses of the products and the continuing development of new applications, the purchaser should carefully consider the suitability and performance of the product for each intended use, and the purchaser shall assume all risks regarding such use. The seller shall not be liable for damages in excess of the purchase price of the product nor for incidental or consequential damages. All specifications are subject to changes without prior notice.